

# TOP GLOVE SDN BHD

## Test Report

**Customer** PROFI PENTRU SANATATE SRL  
**Brand** PPS  
**Sales Order** 2000100036  
**Customer PO** TG001/20  
**Type of Glove** LATEX POWDERED GLOVE (Smooth / Embossed Inside, Natural)  
**AQL Required** 1.5  
**Date of release** 24.06.2020  
**Reference Standard** The above consignment of goods have been inspected against Top Glove Standard where samples selected at random using Single Sampling Plans for Normal Inspection of ISO 2859-1.  
**Declared** Quantity, Size, Lot No., Manufacturing Date, Expiry Date

COA2614/2000100036/000

Size	Quantity (Carton)	Quantity (Pieces)	Lot No.	Manufacturing Date	Expiry Date
L	30	30,000	214100036LPZA	2020-06	2025-05
<b>TOTAL</b>	<b>30</b>	<b>30,000</b>			

Characteristics	Size	Unit	Inspection Level	Acceptance	Result
<b>Freedom From Holes</b>	L	PC	GI	AQL 1.5	PASS

Characteristics	Size	Unit	Inspection Level	Acceptance	Result
<b>Major Visual Defect</b>	L	PC	GI	AQL 2.5	PASS

Characteristics	Size	Unit	Inspection Level	Acceptance	Result
<b>Minor Visual Defect</b>	L	PC	GI	AQL 4.0	PASS

Characteristics	Size	Unit	Sample Size	Non-Compliant	Acceptance	Min. Value	Max. Value	Result
<b>Glove Length</b>	L	mm	13	0	S2_4.0MV 1	244	248	PASS

Characteristics	Size	Unit	Sample Size	Non-Compliant	Acceptance	Min. Value	Max. Value	Result
<b>Glove Palm Width</b>	L	mm	13	0	S2_4.0MV 1	104	106	PASS

Characteristics	Size	Unit	Sample Size	Non-Compliant	Acceptance	Min. Value	Max. Value	Result
<b>Fingertip Thickness</b>	L	mm	13	0	S2_4.0MV 1	0.10	0.11	PASS

Characteristics	Size	Unit	Sample Size	Non-Compliant	Acceptance	Min. Value	Max. Value	Result

**Palm Thickness**

L	mm	13	0	<b>S2_4.0MV</b>	1	0.08	0.09	PASS
---	----	----	---	-----------------	---	------	------	------

ASTM D3578-19 Requirement:

Length (mm):  
XS, S : Min. 220  
M, L, XL, XXL : Min. 230

Width (mm):  
XS: 70 ± 10  
S: 80 ± 10  
M: 95 ± 10  
L: 111 ± 10  
XL: 120 ± 10  
XXL: 130 ± 10

Thickness (Fingertip & Palm):  
Min. 0.08mm

Characteristics	Size	Unit	Sample Size	Non-Compliant	Acceptance	Min. Value	Max. Value	Result
<b>Tensile Strength Before Aging</b>					<b>S2_4.0MV</b>			
	L	MPa	13	0	1	19.2	22.8	PASS
Characteristics	Size	Unit	Sample Size	Non-Compliant	Acceptance	Min. Value	Max. Value	Result
<b>Tensile Strength After Aging</b>					<b>S2_4.0MV</b>			
	L	MPa	13	0	1	16.1	19.4	PASS
Characteristics	Size	Unit	Sample Size	Non-Compliant	Acceptance	Min. Value	Max. Value	Result
<b>Elongation Before Aging</b>					<b>S2_4.0MV</b>			
	L	%	13	0	1	691.9	722.7	PASS
Characteristics	Size	Unit	Sample Size	Non-Compliant	Acceptance	Min. Value	Max. Value	Result
<b>Elongation After Aging</b>					<b>S2_4.0MV</b>			
	L	%	13	0	1	665.2	693.7	PASS

ASTM D3578-19 Requirement:

Before Aging:  
Tensile Strength: Min. 18 MPa  
Elongation at Break: Min. 650%

After Aging:  
Tensile Strength: Min. 14 MPa  
Elongation at Break: Min 500%

Characteristics	Size	Unit	Sample Size	Mean Value	Result
<b>Powder Amount (Powdered Glove)</b>			<b>FIXTR_2</b>		
	L	mg/dm <sup>2</sup>	2	8.53	PASS

Requirement : Max. 10mg/dm<sup>2</sup>**Conclusion**

We hereby certify that glove consignment of goods were determined to meet the acceptable limit of the specifications as referring to the above findings of randomly selected samples.

**Prepared By**  
NURHAFINA BT. ASPAR  
OFFICER, QA

**Approved By**  
LAILAH SYUKRIAH  
ASSISTANT MANAGER, QA

**This is a computer generated test report, no signature is required.**

